

## Amorim Wise Dekwall

Surfaces Collection

Amorim Wise Dekwall wall coverings are made entirely of cork, comprising two layers of 100% natural and renewable raw material – a thick core layer made of agglomerated cork as a backing and a thin sheet of genuine cork veneer for its decorative design. Each panel is coated with a protective finishing for added durability.

Thickness

3 mm

Dimensions


300 × 600 mm

### Characteristics



#### Sustainable

Harvested and made from the bark of cork oak, the tree itself is left intact.




#### Impact Resistant

High shock absorption makes cork resilient to damage from impact.



#### Sound Absorption

Cork reduces noise transmission within rooms for a quieter environment.



#### Energy Efficient

A natural thermal insulator, cork also helps stabilise the temperature in a room.


# PANELOGUE

# Technical Datasheet


Finishes  
Ex-Stock




81000061  
Fiord Exclusive Waxed



81000062  
Hawai Black Pearl Waxed



81000063  
Hawai Black Oyster Waxed



81000071  
Melville Waxed



81000080  
Cayman Waxed




81000106  
Stone Art Platinum

Finishes  
Indent Order



81000000  
Fiord White Waxed



81000058  
Fiord Natural Waxed




81000056  
Flores White Waxed



81000001  
Malta Moonlight Waxed



81000065  
Malta Platinum Waxed



81000066  
Malta Chestnut Waxed



# PANELOGUE

# Technical Datasheet



81000067  
Malta Champagne Waxed



81000074  
Bali Waxed



81000004  
Bamboo Artica Varnished



81000094  
Bamboo Terra Varnished



81000095  
Bamboo Toscana Varnished



81000087  
Hawai Exclusive Waxed



81000088  
Hawai White Waxed



81000057  
Hawai Natural Waxed



81000102  
Stone Art Oyster



81000104  
Stone Art Pearl

## Technical Specifications

Properties	Standard	Unit	Result
Thickness	ISO 7322	mm	3.0 ± 0.3%
Squareness	EN 427	mm	600: < 1.0 mm 300: < 0.5 mm
Density	EN 672	Kg/m <sup>3</sup>	200
Dimension Stability	EN 434	%	3.0 ± 0.3%
Curling	EN 434	mm	≤ 6
Moisture Content	EN 12105	%	≤ 7
Emission	EN 12149 Method C	Class	E1: Low formaldehyde emission
		mg/kg	≤ 95
Vinyl Chloride Monomer (VCM)	EN 12149 Test B	mg/kg	≤ 0.2
Thermal Resistance	EN 12667	m <sup>2</sup> K/W	0.0583(Waxed) 0.0572 (Varnished)
Sound Absorption	ISO 354	α <sub>w</sub>	0.10
Reaction of Heavy Metals and Specific Elements	EN 12149		Fulfilled